

Recycling and Sustainable Development

www.rsd.tfbor.bg.ac.rs



Online ISSN 2560-3132 Print ISSN 1820-7480

Effect of Mechanically Activated Recycled Concrete Powder on The Properties of Cement Paste

Roland Szabó #, Péter Tamás Bárány, Noémi Németh, Mária Ambrus, Gábor Mucsi

^a University of Miskolc, Institute of Raw Materials Preparation and Environmental Technology, Miskolc, Hungary

ARTICLE INFO

Received 31 January 2025 Accepted 13 May 2025

Research article

Keywords: Recycled concrete powder Compressive strength Mechanical activation Rheology Setting time

ABSTRACT

This study investigates the effect of mechanically activated recycled concrete powder (RCP) on Portland cement mixtures with an RCP content of 20 % is investigated. The setting time tests showed that the inclusion of RCP increased the setting time in almost all cases. However, better results were achieved with the mechanically activated RCP than with the RCP raw material additive. In addition, the final setting time was reduced by almost one hour overall (from 380 min to 325 min) when the 3 minute grind was used, which had a similar setting time to Portland cement. The mixtures showed similar behavior in the rheological tests, with the initial shear stress decreasing slightly after the addition of the RCP. Overall, the compressive strength of the RCP-containing mixtures decreased compared to the cement-containing samples. However, a positive effect of milling was observed, as the lowest compressive strength reduction of 29.34 % was achieved by the RCP ground for 3 minutes.

1. Introduction

In recent years, urbanization has increased extremely worldwide and reached 57 % (World Bank Data, 2018). Such an increase in urbanization and urban transformation is leading to the generation of enormous amounts of construction and demolition waste (CDW) due to construction activities of new buildings and infrastructure, reconstruction or renovation, road construction, expansion of existing structures, maintenance and demolition of dilapidated buildings (Ilcan et al., 2023). Since concrete is one of the most extensively used materials in the world, it is not surprising that concrete waste is one of the largest amounts of CDWs. Worldwide, about 10 billion tons of CDW are generated annually (Ilcan et al., 2023), while in the European Union (EU) in 2022, about 850 million tons (38.4 % of the total waste) were generated in the construction industry (Eurostat, 2022), and this trend shows continuous growth. It is estimated that approximately 35 % of CDW is disposed of in landfills annually without further treatment (Menegaki and Damigos, 2018), despite increasing efforts to recycle and reuse CDW (Luciano et al., 2022). CDW can be recycled in various applications, for example, as aggregates in non-structural concrete (Lotfi et al., 2015; Trivedi et al., 2025), filler material in road bases (Tavira et al., 2020; Khan et al., 2024), subgrades (Zhang et al., 2020), an adsorbent material (dos Reis et al., 2020; Pallewatta et al., 2023), and soil conditioner (Santos and Tubino, 2021; Greinert et al., 2024). Recently, extensive research has also been conducted on the utilization of CDW in

[#] Corresponding author: <u>roland.szabo@uni-miskolc.hu</u>

geopolymer/geopolymer concrete applications (Tan et al., 2020).

Concrete waste is mainly used as a coarse aggregate to produce new concrete. The use of recycled concrete aggregate (RCA) in concrete production is limited to low-strength concrete due to difficulties in quality control and poor strength. On the other hand, during the preparation of waste concrete, concrete powder (CP) as a fine (dust) size fraction ($< 75 \,\mu$ m) is generated in appr.10 wt. % (Figueiredo et al., 2018). The CP, which is mainly derived from the cement stone part of concrete, can be used as a replacement material for cement (Cantero et al., 2020; Dacić et al., 2023; Deng et al., 2023). However, the reactivity of recycled concrete powder (RCP) in its current form is low and should be improved so it can be used as a pozzolanic material. Mechanical activation (MA) is one of the effective ways to improve the reactivity of solid materials, as a result of which, in addition to the decrease in particle size and increase in specific surface area, the structure of the material may usually become disordered and defects or other metastable forms may be formed (Juhász and Opoczky, 1990). For MA, different mills can be used like planetary mills (Chen et al., 2021; Wu et al., 2022; Gao et al., 2025), ball mills (Cantero et al., 2020; Kong et al., 2025), and stirred media mills (Mucsi et al., 2021; Szabó et al., 2023). At the same time, the optimal fineness is very important, as the fineness of the RCP has a strong influence not only on the hydration process (Chen et al., 2021; Li et al., 2022; Deng et al., 2023; Xue et al., 2025) and, thus, the strength (Cantero et al., 2020; Chen et al., 2021; Mucsi et al., 2021; Du et al., 2023), but also on the workability (Cantero et al., 2020; Deng et al., 2023) and setting time (Wu et al., 2022; Li et al., 2023). From the literature, it can be concluded that the ball mill is most commonly used to produce RCP, but only a few studies (Mucsi et al., 2021; Szabó et al., 2023) deal with the properties of products made using RCP produced in a high-energy density mill (e.g. stirred media mill).

The research aims to investigate the effect of mechanical activation of RCP in a high-energy density mill on the setting time and rheology of the cement paste and to study the relationships between the mechanically activated RCP and the properties of the new product.

2. Material and methods

2.1. Material characterization

The RCP from waste concrete and Portland cement were used for the experiments. The initial particle size of the waste concrete was <20 mm (median particle size, $x_{50}=6.0$ mm) and it came from Mento Ltd.

(Bodrogkeresztúr, Hungary), while the cement was slag Portland cement with a high initial strength of 42.5 MPa standard strength according to MSZ EN 197-1 (CEM II/A-S 42.5 R), from LAFARGE-Cement Hungary Ltd, Hungary. The main characteristic particle sizes of the cement were as follows: x_{10} =5.57 µm, x_{50} =12.74, and x_{90} =24.69 µm.

Several studies have found that impact, rubbing, and abrasion can be effective solutions for removing mortar adhering to the surface of aggregates (Nagataki et al., 2004; Quan, 2011; Tam et al., 2021). However, during mechanical grinding, the RCA can be more easily damaged and broken into finer fractions, increasing its proportion in the cement stone powder and thereby degrading the properties of the RCP (Tam et al., 2021).

Considering all this, to recover the RCP, as a first step, the fine fraction (<200 microns) was removed with sieving, and then the coarse fraction was subjected to low-energy selective milling (SM) in a laboratory-scale drum mill at low speed (50 rpm) for 60 min, as a result of which the kinetics of fragmentation occur by autogenous abrasion.

Due to the abrasion of the concrete, a higher amount of RCP could be obtained, which was sieved below 200 μ m.

The particle size distribution (PSD) of the RCP was measured with a HORIBA LA-950V2 laser diffraction particle size analyzer in wet mode using alcohol as dispersing media.

The geometric specific surface area (SSA) was calculated using PSD data by the laser sizer software. The median particle size and SSA of the RCP were found to be 20 μ m and 2715 cm²/g, respectively. The particle density was determined using the pycnometer method, with isopropyl alcohol as the medium. The bulk density and particle density of the RCP were 0.88 and 2.47 g/cm³, respectively.

The mineralogical composition of the RCP, which was determined with a Bruker D8 Advance X-ray powder diffractometer (XRD) (Cu-K α radiation, 40 kV, 40 mA) in parallel beam geometry (Göbel-mirror), is presented in Table 1.

The amorphous content was determined using the amorphous hump method, which has been successfully applied in several research involving silicate rocks (Németh et al., 2023) and alkali activation products (Kumar et al., 2017), where the XRD data was correlated with chemical composition or by direct comparison of the internal standard and the hump method (Ahmad et al., 2018).

Based on Table 1, it can be concluded that a significant proportion of the RCP is quartz and carbonates derived from the fine aggregate (sand) of the waste concrete and hydrated cement.

Table 1

Mineralogical	composition	of RCP	(Szabó et	al., 2023)
---------------	-------------	--------	-----------	------------

Phase name	RCP (wt. %)		
Quartz	54.4		
Muscovite 2M1	4.0		
Calcite	9.7		
Vaterite	6.3		
Albite	6.1		
Orthoclase	3.0		
Chlorite IIb	0.6		
Ettringite	0.3		
Portlandite	0.2		
Actinolite	0.4		
Amorphous	15.0		

2.2. Mechanical activation

The disc-stirred media mill used for MA is equipped with a ceramic liner and a built-in cooling system, and the effective volume of the mill is 530 cm^3 . The filling ratio of both the material and the milling beads (zirconium silicate "ZS type", Ø 1-1.2 mm ceramic beads) was 70 %. The mill was operated at a rotor speed of 5 m/s. The applied milling times were 1, 3, and 5 min.

The 0 min milling refers to the pre-processed raw RCP sample (RCP0) that was not mechanically activated in the stirred media mill. The mechanically activated RCP samples obtained as a result of milling were labeled MARCP1, MARCP3, and MARCP5, where the numbers indicate the milling time.

2.3. Setting time

The initial and final setting times of all pastes were tested according to the Hungarian standard (MSZ EN 196-3, 2017) using a standard Vicat apparatus. The water/binder (w/b) ratio was 0.33 in all cases. The RCP replacement rate was determined based on previous research (Szabó et al., 2023). Based on this, 20 % of the solid material (cement) of the paste was replaced by RCP of different fineness obtained during MA. The consistency and flowability of all samples were appropriate for the Vicat setting time tests. The paste was placed into the Vicat mold, and the Vicat needle was lowered into the paste at regular intervals. The initial setting time was recorded when the penetration was no longer possible at a specified depth (distance between the

needle and the glass plate 4 ± 1 mm), while the final setting time was recorded when the needle did not sink more than 0.5 mm into the hardened cement paste. As a reference, the setting time of the cement paste (CP) without RCP was also investigated.

2.4. Rheology

The flowability of the pastes was determined by measuring the change in shear stress as a function of the change in shear rate (s⁻¹) at a given RCP content (20 % w/w) but at different RCP finenesses using an Anton Paar Physica MCR 51 type rotational rheometer with cylinder-cylinder measuring head. The shear rate was 1000...100 s⁻¹, starting at the highest shear rate value to avoid the sedimentation of small particles during the test. The rheometer is equipped with the Rheoplus data collector software to record the shear stress values. For reference, the rheology of the CP without RCP was also studied. The w/b ratio was 0.38 in all series. Furthermore, two measurements were taken for each series, and the values obtained were averaged.

2.5. Mechanical strength

The specimens used for strength tests were obtained by mixing cement, RCP, and water. The w/b ratio was kept at 0.33. The pastes were cast in cubic molds and compacted for 1 minute on a vibrating table. After 24 hours, the specimens were de-molded and stored under water until the compressive strength test. The uniaxial compressive strength of 20 mm cube specimens was tested at the age of 7 days using an SZF-1 type hydraulic compression testing machine with a maximum load of 25 kN. Five specimens were tested in each series and the strength values were averaged.

2.6. Structure

Structural analyses of the mechanically activated RCP and hardened pastes were performed by Fourier Transform Infrared (FTIR) spectroscopy, by which bending and stretching vibrations of chemical bonds in the samples were detected by a JASCO FT-IR 4200 type Fourier Transform Infrared Spectrometer in reflection mode and a diamond ATR.

After the mechanical strength tests, the powdered samples and pieces of the broken specimens were crushed in a mortar to a suitable particle size (~15-50 μ m) for effective FTIR testing. The spectra were recorded in the absorption range from 4000 to 400 cm⁻¹. The spectra were baseline corrected, and each spectrum was an average of the results of 3 runs.

3. Results and Discussion

3.1. Mechanical activation

The effect of MA on the particle size distribution of RCPs can be seen in Figure 1, while the characteristic particle sizes $(x_{10}, x_{50}, and x_{90})$ and the "outer" geometric SSA of RCPs are shown in Table 2. Based on the results, it can be stated that milling resulted in a decrease in the particle size of MARCPs, while the SSA increased.

However, after 1 minute of milling, there was no significant reduction in the particle size of the MARCP, which can be attributed to the phenomenon of aggregation and agglomeration. A significant amount of the small particles (a few hundred nanometers) produced during milling adhered to each other and to larger particles (about 100 microns), increasing in particle size, and therefore no significant change in SSA. Similar statements were made by Zhang et al. (2022), who found that mechanical activation (in a planetary ball mill) helped to modify the particle size and distribution of RCP. At the same time, it was observed that beyond a certain grinding time (60 min), the reduction in particle size was not significant, which did not result in an increase in strength.



Figure 1. Particle size distribution by volume of the RCPs

Table 2

The characteristic particle size and SSA values of the raw and mechanically activated RCPs

Milling time (min)	x ₁₀ (μm)	x ₅₀ (μm)	x ₉₀ (μm)	SSA (cm²/g)
0	3.28	20.22	126.67	2,715
1	1.64	8.42	98.80	8,614
3	1.51	6.67	129.20	10,070
5	1.22	7.65	159.40	10,832

3.2. Setting time

The incorporation of RCP has a two-sided effect on the setting time of the paste. On the one hand, the incorporation of RCP reduces the amount of hydrated products in the paste, thereby increasing the setting time (Wu et al., 2022; Zhang et al., 2023). On the other hand, particles function as crystallization nuclei, RCP promoting the formation of hydration products and reducing the setting time (Tang et al., 2020; Wu et al., 2022; Kaptan et al., 2024). Figure 2 shows the initial and final setting times of the paste containing RCP with different fineness. The setting time results showed that the inclusion of the RCP increased the setting time in all cases. In particular, when using low fineness RCP0, the increase in setting time is more noticeable due to the reduction of hydration products in the paste. However, when MARCPs were used, both the initial and final setting times of the paste were shorter compared to the RCP0-containing paste. Compared to CP, the initial and final setting times of RCP0-CP increased by 23.3 % and 18.8 %, respectively, while the initial and final setting times of MARCP3-CP only increased by 7.0 % and 1.5 %, respectively. A similar finding was made by Zhao et al. (2020) and Wu et al. (2022), according to whom highfineness recycled brick powder and RCP helped to reduce the initial and final setting time of the paste, as the high reactivity of the brick powder and RCP accelerated the formation of hydration products. It can also be seen that the initial setting time of MARCP5-CP was the same as that of MARCP3-CP, but the final setting time was significantly longer than that of MARCP3-CP. This can be explained by the fact that the more reactive fine particles of MARCP5 accelerated the initial setting time as a result of more intense hydrated product formation, while the presence of agglomerated coarse particles resulted in the formation of less hydrated product in the later setting phase, thereby increasing the final setting time.



Figure 2. Setting time of the paste with different rcp fineness

3.3. Rheology

Figure 3 shows the flow curves of the plain CP and CP with a different fineness of RCP. From Figure 3, it can be concluded that the blends showed similar behavior during the rheological tests according to the Herschel-Bulkley model, with a slight decrease in initial shear stress after the addition of RCP. No clear trend can be observed in the flow behavior of the pastes when using RCPs of different fineness, but it can be related to the particle size and SSA of MARCPs. MARCP1-CP showed similar flow behavior to CP, while RCP0-CP had the lowest flow resistance. According to Deng et al. (2023), the fluctuation of the rheological parameters of cement pastes is closely related to the dosage and fineness of the RCP. They found that the yield stress and plastic viscosity of cement paste significantly increased with the increase of recycled fine powder (RFP) content.

This can be explained on the one hand by the fact that the RFP particles resulted in higher water absorption and less free water in the slurry, on the other hand, due to the wider particle size distribution and more regular surface morphology of the RCP particles, there is less possibility of friction and adhesion between the particles during the shear test.



Figure 3. Flow curves of the pastes with different RCP fineness

3.4. Mechanical strength

Figure 4 presents the compressive strength of paste including RCP at different fineness. From this Figure, it can be concluded that the addition of RCP at different fineness resulted in lower strength in all cases compared to the CP sample. However, the positive effect of MA was observed, as the lowest compressive strength decrease of 29 % was achieved by MARCP3-CP when the strength value decreased from 68.8 MPa to only 48.6 MPa. The sample with the non-activated RCP content (RCP0-CP) had the lowest strength (39.4 MPa). This is also supported by the findings of Wu et al. (2022) that the negative effect of coarse RCP on mechanical strength is greater than the negative effect of fine RCP on mechanical strength. This is because the use of coarse RCP can reduce the filler effect and pozzolanic activity of RCP. The positive effect on mechanical strength can be explained by the fact that the more reactive, finer RCP improved the dissolution and precipitation process of cement hydration, thereby creating a denser (less porous) structure (Deng et al., 2023). At the same time, it can also be stated that with the extension of grinding time, the agglomeration effect between RCP particles was enhanced, which weakened the filling effect of RCP and adversely affected the strength of MARCP5-CP (Shen et al., 2023). Xue et al. (2025) found that as the RCP particle size decreased, the RCP activity index first increased and then decreased, indicating that the fineness of RCP is not better, the finer, and there is an optimal fineness. They also stated that RCP mainly exerts a physical filling and nucleation effect and some puccolan effect on the cement-RCP system. The smaller RCP particle size provides more nucleation sites for cement and hydration products.



Figure 4. Compressive strength of the samples

3.5. Structure

The FTIR spectra of the cement and RCPs with different fineness can be seen in Figure 5. In the case of the cement spectrum, the bands at 1428 and 873 cm⁻¹ can be assigned to CO_3^{2-} stretching vibrations. The weak band at 1,113 cm⁻¹ is the indication of Si–O–Si stretching vibrations, and the band at 521 cm⁻¹ corresponds to the Si–O deformation vibrations of the siliceous phases

(Amor et al., 2018; Cho et al., 2018; Szabó et al., 2023). The spectra of the RCP0 and MARCPs show prominent vibrations at 1,428, 1,010, and 874 cm⁻¹, respectively, which can be attributed to $v3-CO_3^{2-}$ stretching, Si-O-Si stretching, and v2-CO₃²⁻ stretching vibrations; these arise from the CaCO₃ and calcium silicate (C_3S and C_2S) phases, which are the main constituents of cement (Cho et al., 2018; Li et al., 2025). The broad band at \sim 3416 cm⁻ ¹ in the spectrum of RCPs corresponds to the O-H stretching, and the weak band at 1614 cm⁻¹ corresponds to the O-H bending vibration, indicating the presence of small amounts of structural and weakly bound water in the samples. The bands at 796, 779, and 694 cm⁻¹ show the presence of quartz (Mucsi et al., 2021). Compared to the RCP0 sample, the FTIR spectra of MARCPs show a difference in the intensity of some bands. As a result of milling, the intensity of bands (796, 779, and 694 cm⁻¹) referring to quartz decreased.



Figure 5. FTIR spectra of the cement and RCPs with different fineness

Figure 6 shows the FTIR spectra of the cement pastes. The bands referring to hydrated phases are discernible in the spectra of all samples. The wide band at around 3,375 cm⁻¹ is attributed to the symmetric stretching vibration of the H₂O molecule, while the narrow, unique band at 3,640 cm⁻¹ can be assigned to the presence of portlandite (Ca(OH)₂) (Horgnies et al., 2013; Lu et al., 2018). It can also be seen that in each paste there are two strong bands between 1,430 cm⁻¹ and 873 cm⁻¹, which can be attributed to the in-plane and out-of-plane bending vibrations of CO₃²⁻, respectively. Additionally, the bands at 1,416 and 873 cm⁻¹ were wide, which was clear evidence of the presence of amorphous CaCO₃ (Lu et al., 2018; Li et al., 2025). The intensity of these bands is greater in the case of finer MARCP-containing pastes. The band at around 960 cm⁻¹ refers to Si-O stretching vibrations, indicating a wide range of C-S-H with Ca/Si \approx 2 (Pan et al., 2017). The intensity of this band can be related to the fineness of the RCP. The MARCP1-CP sample had the highest band intensity.



Figure 6. FTIR spectra of the specimens

6. Conclusions

This paper investigates the influence of RCP of different fineness on the early cementing behavior and performance of hardened cement paste. Based on the experimental results, the following conclusions can be drawn:

- 1. Compared to cement, RCP has a wider particle size distribution and a significant SiO₂ content (mainly quartz). The inert components in RCP resulted in low activity.
- 2. When MARCP was used, both the initial and final setting times of the cement paste were shorter than for the paste with RCP0, as MARCP with higher reactivity accelerates the formation of hydration products.
- 3. The finer particles of MARCP improved the rheological properties of the paste due to their higher water absorption capacity, which reduced the free water in the slurry.
- 4. The use of RCP resulted in a lower performing CP. However, the MARCP-CPs showed better strength compared to the RCP0-CP. At the same time, the optimization of the mechanical activation process is very important as there was significant aggregation and agglomeration of the particles after 1 minute of milling, resulting in a lower strength of the sample due to the reduced dissolution and precipitation process of cement hydration.

Acknowledgment

The research work was performed in the Centre of Excellence in Sustainable Natural Resource Management at the Faculty of Earth Science and Engineering, University of Miskolc. This study was carried out within the framework of project no. 2019-2.1.7-ERA-NET-2022-00051 entitled "Foamed Geopolymer Made by Additive Manufacturing for the Construction Technology Applications" with support from the National Research, Development and Innovation Fund of

the Ministry of Culture and Innovation and Hungarian Organizations, in the financing of the ERA-NET COFUND /EJP COFUND Program with co-funding from the European Union Horizon 2020 research and innovation program.

The authors thank the Department of Mining and Geotechnical Engineering of the University of Miskolc for their help during the mechanical strength tests and the Department of Mineralogy and Geology for the XRD analysis of RCP.

References

- Ahmad K. M., Kristály F., Turzó Z., Effects of clay mineral and physico-chemical variables on sandstone rock permeability, Journal of Oil, Gas and Petrochemical Sciences, 1(1), 2018, 18-26,
- Amor F., Diouri A., Ellouzi I., Ouanji F., Development of Zn-Al-Ti mixed oxides-modified cement phases for surface photocatalytic performance, Case Studies in Construction Materials, 9, 2018, e00209,
- Cantero B., Bravo M., de Brito J., Sáez del Bosque I. F., Medina C., Mechanical behavior of structural concrete with ground recycled concrete cement and mixed recycled aggregate, Journal of Cleaner Production, 275, 2020, 122913,
- Chen X., Li Y., Bai H., Ma L., Utilization of recycled concrete powder in cement composite: strength, microstructure and hydration characteristics, Journal of Renewable Materials, 9 (12), 2021, 2189-2208,
- Cho J., Waetzig G. R., Udayakantha M., Hong C. Y., Banerjee S., Incorporation of hydroxyethylcellulosefunctionalized halloysite as a means of decreasing the thermal conductivity of oilwell cement, Scientific Reports, 8, 2018, 16149,
- Dacić A., Fenyvesi O., Kopecskó K., Investigation of waste perlite, recycled concrete powders as supplementary cementitious materials, Periodica Polytechnica Civil Engineering, 67 (3), 2023, 683– 694,
- Deng X., Li J., Lu Z., Zhang J., Luo K., Niu Y., Hu J., He K., Rheological and early hydration of cementitious material containing recycled concrete powders collected from recycled aggregates, Construction and Building Materials, 393, 2023, 132108,
- dos Reis G. S., Grigore Cazacliu B., Rodriguez Correa C., Ovsyannikova E., Kruse A., Hoffmann Sampaio C., Lima E. C., Dotto G. L., Adsorption and recovery of phosphate from aqueous solution by the construction and demolition wastes sludge and its potential use as phosphate-based fertilizer, Journal of Environmental Chemical Engineering, 8 (1), 2020, 103605,
- Du J., Zhang T., Chen P., Guo Y., Zhan B., Wei J., Yu Q., Phase separation of recycled concrete powder during grinding and consequent influences on its hydration behaviors in cement paste, Cement and

Concrete Composites, 142, 2023, 105203,

- Eurostat, Waste statistic European Commission, 2022. <u>https://ec.europa.eu/eurostat/statistics-</u> <u>explained/index.php?title=Waste_statistics#Total_w</u> <u>aste_generation</u>, overtaken 12.05.2024.
- Figueiredo P. O., Ulsen C., Bergerman M. G., Mucsi G., Properties of recycled concrete aggregate produced by different comminution methods, Proceedings of the International V4 Waste Recycling 21 Conference, Miskolc, Hungary, November 2018, 219–227., Editor: Bokányi L., Publisher: University of Miskolc, ISBN 978-963-358-173-5,
- Gao Q., Li X., Shi X., Li X., Lyu X., Zhu X., Ren Y., Clean and high-value recycling approach for waste concrete powder: Mechano-chemical activation of pozzolanic activity, Powder Technology, 458, 2025, 120988,
- Greinert A., Piernik A., Grande U., Hulisz P., Construction and demolition waste (CDW) in urban soils as a factor controlling their diversity, Geoderma, 449, 2024, 117019,
- Horgnies M., Chen J. J., Bouillon C., Overview about the use of Fourier transform infrared spectroscopy to study cementitious materials, WIT Transactions on Engineering Sciences, WIT Press, 77, 2013, 251–262,
- Ilcan H., Sahin O., Kul A., Ozcelikci E., Sahmaran M., Rheological property and extrudability performance assessment of construction and demolition wastebased geopolymer mortars with varied testing protocols, Cement and Concrete Composites, 136, 2023, 104891,
- Juhász A. Z., Opoczky L., Mechanical activation of minerals by grinding. Pulverizing and morphology of practices, Budapest: Akadémiai Kiadó – Chichester: Ellis Horwood Ltd Publishers, 1990. ISBN: 0745800157,
- Kaptan K., Cunha S., Aguiar J., A Review of the Utilization of Recycled Powder from Concrete Waste as a Cement Partial Replacement in Cement-Based Materials: Fundamental Properties and Activation Methods, Applied Sciences, 14 (21), 2024, 9775,
- Khan Z. A., Balunaini U., Costa S., Nguyen N. H.T., A review on sustainable use of recycled construction and demolition waste aggregates in pavement base and subbase layers, Cleaner Materials, 13, 2024, 100266,
- Kong, X., Yao Y., Kai M., Guan Y., Ding X., Gu Z., Liu J., The assessment of the mechanical and durability properties of mortar prepared with carbon dioxidetreated recycled concrete-brick powder, Construction and Building Materials, 466, 2025, 140305,
- Kumar S., Mucsi G., Kristály F., Pekker P., Mechanical activation of fly ash and its influence on micro and nano-structural behaviour of resulting geopolymers. Advanced Powder Technology, 28 (3), 2017, 805– 813,
- Li Z., Bian Y., Zhao J., Wang Y., Yuan Z., Recycled

concrete fine powder (RFP) as cement partial replacement: influences on the physical properties, hydration characteristics, and microstructure of blended cement, Journal of Building Engineering, 62, 2022, 105326,

- Li J., Zhan B., Gao P., Hu L., Qiao M., Sha H., Yu Q., Effects of recycled concrete powders on the rheology, setting and early age strength of cement paste, Construction and Building Materials, 401, 2023, 132899,
- Li X., Wang X. Y., Li M., Zhan Q. W., Dong W. Y., Study on activation and performance of recycled hardened concrete powder based on microbial accelerated carbonization, Biochemical Engineering Journal, 214, 2025, 109586,
- Lotfi S., Eggimann M., Wagner E., Mróz R., Deja J., Performance of recycled aggregate concrete based on a new concrete recycling technology, Construction and Building Materials, 95, 2015, 243–256,
- Lu B., Shi C. Zhang J. Wang J., Effects of carbonated hardened cement paste powder on hydration and microstructure of Portland cement, Construction and Building Materials, 186, 2018, 699–708,
- Luciano A., Cutaia L., Altamura P., Penalvo E., Critical issues hindering a widespread construction and demolition waste (CDW) recycling practice in EU countries and actions to undertake: the stakeholder's perspective, Sustainable Chemistry and Pharmacy, 29, 2022, 100745,
- Menegaki M., Damigos D., Review on current situation and challenges of construction and demolition waste management, Current Opinion in Green and Sustainable Chemistry, 13, 2018, 8–15,
- Methods of testing cement. Part 3: Determination of setting times and soundness, MSZ EN 196-3:2017 Standard, 2017,
- Mucsi G., Halyag Papné N., Ulsen C., Figueiredo P. O., Kristály F., Mechanical activation of construction and demolition waste in order to improve its pozzolanic reactivity, ACS Sustainable Chemistry & Engineering, 9 (9), 2021, 3416–3427,
- Nagataki S., Gokce A., Saeki T., Hisada M., Assessment of recycling process induced damage sensitivity of recycled concrete aggregates, Cement and Concrete Research, 34 (6), 2004, 965–971,
- Németh N., Kristály F., Gál P., Móricz F., Lukács R., Metavolcanic formations in the Paraautochthonous Triassic successions of the Bükk Mts, NE Hungary, International Journal of Earth Sciences (Geol Rundsch) 112, 2023, 297–320,
- Pallewatta S., Weerasooriyagedara M., Bordoloi S., Sarmah A.K., Vithanage M., Reprocessed construction and demolition waste as an adsorbent: an appraisal, Science of The Total Environment, 882, 2023, 163340,
- Pan X., Shi C., Hu X., Ou Z., Effects of CO₂ surface treatment on strength and permeability of one-day-

aged cement mortar, Construction and Building Materials, 154, 2017, 1087–1095,

- Quan H. Z., Effects of Adhered Mortar Content on Quality of Recycled Coarse Aggregate of Concrete, Advanced Materials Research, 194–196, 2011, 1059– 1062,
- Santos R. P., Tubino R., Potential evaluation of the use of construction and demolition waste (CDW) in the recovery of degraded soils by mining in Brazil, Resources, Conservation & Recycling Advances, 12, 2021, 200060,
- Shen Z., Zhu H., Zhao Z., Pang S., Li Z., Yang S., Cao P., Lin S., High-performance artificial aggregate prepared with recycled concrete powder and its impact on concrete properties, Construction and Building Materials, 404, 2023, 133151,
- Szabó R., Szűcs M., Ambrus M., Mucsi G., Increasing the pozzolanic reactivity of recovered CDW cement stone by mechanical activation, Materials Proceedings, 13 (1), 2023, 27,
- Tam V.W.Y., Soomro M., Evangelista A.C.J., Quality improvement of recycled concrete aggregate by removal of residual mortar: A comprehensive review of approaches adopted. Construction and Building Materials, 288, 2021, 123066,
- Tan J., Cai J., Li X., Pan J., Li J., Development of ecofriendly geopolymers with ground mixed recycled aggregates and slag, Journal of Cleaner Production, 256, 2020, 120369,
- Tang Q., Ma Z., Wu H., Wang W., The utilization of ecofriendly recycled powder from concrete and brick waste in new concrete: A critical review. Cement Concrete. Composites. 114, 2020, 103807,
- Tavira J., Jiménez J. R., Ledesma E. F., López-Uceda A., Ayuso J., Real-scale study of a heavy traffic road built with in situ recycled demolition waste, Journal of Cleaner Production, 248, 2020, 119219,
- The World Bank Data, Urban population (% of the total population), 2018 revision, https://data.worldbank.org/indicator/SP.URB.TOTL. IN.ZS, date of access 12.08.2024.
- Trivedi S. S., Das B. B., Barbhuiya S., Performance of construction and demolition waste as recycled aggregates in concrete – review, Proceedings of the Institution of Civil Engineers - Construction Materials, 178 (1), 2025, 20–47,
- Wu H., Liang C., Xiao J., Xu J., Ma Z., Early-age behavior and mechanical properties of cement-based materials with various types and fineness of recycled powder, Structural Concrete, 23(2), 2022, 1253– 1272,
- Xue C., Tian G., Zhang Y., Wang Z., Qiao H., Su L., Study on the effect of particle size on the basic characteristics of RCP and hydration kinetics of slurry, Construction and Building Materials, 470, 2025, 140540,
- Zhang J., Ding L., Li F., Peng J., Recycled aggregates

from construction and demolition wastes as alternative filling materials for highway subgrades in China, Journal of Cleaner Production, 255, 2020, 120223,

Zhang D., Zhang S., Huang B., Yang Q., Li J., Comparison of mechanical, chemical, and thermal activation methods on the utilisation of recycled concrete powder from construction and demolition waste, Journal of Building Engineering, 61, 2022, 105295,

- Zhang H., Zhang C., He B., Yi S., Tang L., Recycling fine powder collected from construction and demolition wastes as partial alternatives to cement: A comprehensive analysis on effects, mechanism, cost and CO₂ emission. Journal of Building Engineering, 71, 2023, 106507,
- Zhao Y., Gao J., Liu C., Chen X., Xu Z., The particle-size effect of waste clay brick powder on its pozzolanic activity and properties of blended cement, Journal of Cleaner Production, 242, 2020, 118521.

Uticaj mehanički aktiviranog praha recikliranog betona na svojstva cementne paste

Roland Szabó[#], Péter Tamás Bárány, Noémi Németh, Mária Ambrus, Gábor Mucsi

^a Univerzitet u Miškolcu, Institut za pripremu sirovina i zaštitu životne sredine, Miškolc, Mađarska

INFORMACIJE O RADU

Primljen 31 januar 2025 Prihvaćen 13 maj 2025

Originalan rad

Ključne reči: Prah recikliranog betona Pritisna čvrstoća Mehanička aktivacija Reologija Vreme vezivanja

IZVOD

Ova studija istražuje uticaj mehanički aktiviranog praha recikliranog betona (PRB) na mešavine portland cementa sa udelom PRB-a od 20 %. Testovi vremena vezivanja pokazali su da dodatak PRB-a produžava vreme vezivanja u gotovo svim slučajevima. Ipak, bolji rezultati su postignuti upotrebom mehanički aktiviranog PRB-a u poređenju sa dodatkom sirovog PRB-a. Pored toga, konačno vreme vezivanja je ukupno smanjeno za skoro jedan sat (sa 380 minuta na 325 minuta) kada je korišćeno mlevenje u trajanju od 3 minuta, pri čemu je postignuto vreme vezivanja slično onom kod portland cementa. Mešavine su pokazale slična ponašanja u reološkim testovima, pri čemu je početni napon smicanja blago opao nakon dodavanja PRB-a. Ukupno posmatrano, pritisna čvrstoća mešavina koje sadrže PRB bila je smanjena u odnosu na uzorke koji sadrže samo cement. Međutim, zabeležen je pozitivan efekat mlevenja, jer je najmanje smanjenje pritisne čvrstoće, od 29,34 %, postignuto PRB-om mlevenim u trajanju od 3 minuta.